

ANQA-DAMP WB

The Elastomeric Damp Waterproof Coat

🌐 www.anqa.com.sa ✉ @anqa_com_sa 📷 [@anqa.com.sa](https://www.facebook.com/anqa.com.sa)



DESCRIPTION:

ANQA-DAMP WB is a single-pack damp-proof coating. It provides flexible waterproofing for wet and damp areas. **ANQA-DAMP WB** has good flexibility and is ideally suited for use over concrete, and it is applied by brush, spray or rubber squeegee.

ANQA-DAMP WB is a blend of weather- and water-resistant pigments, fillers, and co-polymer resins.

ADVANTAGES:

- Waterproof coating.
- Allows surfaces to breathe while maintaining strong adhesion to the substrate.
- Cost-effective solution.

APPLICATION AREAS:

- Waterproof and damp-proof coating for wet areas such as bathrooms, kitchens, and balconies.
- Waterproof and damp-proof coating for underground structures.

APPLICATION METHOD:

Surfaces must be solid and cleaned of any loose particles, grease, or oil.

Priming: Primer must be applied over porous and concrete surfaces, dilute **ANQA-DAMP WB** with an appropriate amount of water as required (approximately 3–4 kg per 20 kg pail)

Coating: Apply the required coats once the primer coat has dried. Apply multiple coats perpendicular to each other. Treat all joints and cracks and reinforce them with fiberglass mesh and suitable filling materials.

COVERAGE:

Apply **ANQA-DAMP WB** by spray, brush or rubber squeegee in two coats, at least, and Approximately 200 microns per coat, resulting in a consumption rate of 1.5–1.8 m²/kg per 1 mm coat.

HEALTH & SAFETY:

Skin & Eye contact: Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

Flammability: Nonflammable and nonhazardous; dried materials may burn.

Cleaning: **ANQA-DAMP WB** is a water-based material; tools can be cleaned by water immediately after use. Dried material can only be removed mechanically.

SHELF LIFE:

12 months for unopened containers. Use older stock first.

TECHNICAL SPECIFICATIONS:

SPECIFICATIONS	TEST METHOD	RESULTS
Appearance		Thick Black Paste
Water Permeability	ASTM-A3245	≈ Zero
Solid Content (%)	ASTM-D 475	60-75%
Specific Gravity		≈1.30 kg/L
Viscosity (Brookfield Spindle: 6, Speed: 20 rpm)		45000-55000 CPs.
Curing Time	ASTM-C 4125	48Hrs
Elongation at Break	ASTM-D 2370-98	>250%