

ANQA POXY AQUA HB

Water Tanks SF Epoxy Lining Coating



🌐 www.anqa.com.sa ✉ @anqa_com_sa 📱 [@anqa.com.sa](https://www.facebook.com/anqa.com.sa)

DESCRIPTION:

POXY AQUA HB is a solvent-free, high-build 2K epoxy coating system for water tanks.

ADVANTAGES:

- solvent free, Waterproof coating
- High-build
- glossy and colorful (Blue, White, Grey RAL)
- chemical resistant
- Supplied in pre-measured packs.

APPLICATION AREAS:

- concrete potable water tanks
- concrete swimming pools
- Steel tanks (requires blasting)

APPLICATION METHOD:

Surfaces must be solid and free of loose particles, grease, and oil.

Priming: If required, primer must be applied over porous and concrete surfaces.

Mixing: mix **POXY AQUA HB** 2 parts (resin + hardener) as per mentioned ratio on the pack.

Use a mechanical mixer to ensure uniform consistency and proper color distribution.

Coating: Apply the required coats once the primer coat has dried. Multiple coats have to be applied perpendicularly.

- All joints and cracks must be treated and reinforced by suitable **ANQA** cement-based or Epoxy-based Repair mortar materials.

- Use airless, brush or roller to apply **POXY AQUA HB**.
- Ensure the required quantity is mixed and avoid using the mixed material (resin + hardener) after 1 hour (pot life).
- Allow the coated surface to cure fully for 7 days before filling with water.

COVERAGE:

2 m²/kg at 400-micron coat

HEALTH & SAFETY:

Skin & Eye contact: Avoid prolonged contact with eyes and skin. For detailed information, refer to the relevant material safety data sheet.

Cleaning: use **ANQA-POXY SOLV.** remover solvent or any suitable solvent to clean tools.

SHELF LIFE:

12 months for unopened containers; use older stock first.

TECHNICAL SPECIFICATIONS:

SPECIFICATIONS	RESULTS
Appearance	Thick colored paint
Water permeability	≈ Zero
Solid Content (%) (Mixture)	100%
Specific gravity	≈1.40 kg/L
Pot life	40-60 minutes @ 20°C
Curing Time:	48 hours
Dust Dry @30°C:	2 hours.
Hard Dry @30°C:	8 hours.
Mixing ratio	4:1 (resin:hardener)
VOC Content (ASTM D3690)	9 gm/kg